Characteristics and applications:

E-10 is an ilmenite type electrode and can be used in all-position welding. It has excellent mechanical properties and X-Ray performance, stable arc, and good weldability. The weld bead is good with deep penetration and hardly causes slag inclusion. The weld metal can meet the elongation request of 22% min. Its features allows the product to be applied to important structural objects such as ship body, boiler, vehicle frame, oil tank, steel frame and suitable for structural steels, steel strip, thin steel plate, fabrication steels which thickness is on or below 25 mm.

Notes on usage:

- 1. Be sure to clean up the contamination on the base metal to reduce the cause of welding defect.
- 2. It is highly recommended to dry the electrodes at 80-100°C for 30-60 minutes before using.
- 3. Apply proper currents to prevent X-Ray and mechanical properties from being worse.
- 4. When you weld with weave method, the moving range should not exceed 3 times the wire dia.

Typical chemical composition of all weld metal (wt%):

С	Mn	Si	Р	S
0.095	0.45	0.08	0.02	0.015

Typical mechanical properties of all weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -20°C (0)
430(62)	490(71)	27	50(37)

Welding position:

Sizes and recommended current range (AC or DC<+>):

Diameter (mm)		2.6	3.2	4.0	5.0
Length (mm)		350	350	450	450
Amps	F	50-100	80-140	130-180	170-240
	\/&OH	40-70	60		

*The information contained or etherwise referenced berein is presented only as "twice" without quarentee on warming the end of the ethode Co. Ltd. expressly disclaims and liability....

in our makers any enhanced there are the independent of the ether and any of the ether and produced threath realizable.

In the end of the ether and the end of the end of the ether and the ether and the ether and produced threath realizable.

