

# R-13

HIGH TITANIA TYPE

AWS A5.1 E6013  
EN ISO 2560-B-E4313 A  
JIS Z 3211 E4313

## Characteristics and Applications:

R-13 is designed for high efficiency welding with thin flux coating. It features good slag release, shallow penetration, less spatters, and smooth bead appearance. It is suitable for welding application of vehicles, steel sheets and other light structures.

## Notes on usage:

1. Proper current range and available with AC or DC welding.
2. Dry the electrode at 80-100°C for 30~60 minutes.
3. Clean up the contaminations on the base metal to reduce the cause of welding defect.
4. Apply proper currents for good X-Ray and mechanical properties.

## Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S
0.07	0.30	0.25	0.025	0.015

## Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) 0°C (32 °)
450(65)	520(75)	25	50(37)

## Welding position:



## Sizes and recommended current range (AC or DC <±>):

Diameter (mm)		1.6	2.0	2.6	3.2	4.0	5.0
Length (mm)		300	300	350	350	450	450
Amps	F	20-50	30-60	60-90	90-130	140-180	160-220
	V&OH	20-40	30-55	50-80	80-100	110-150	140-200

\*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Tien Tai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance on this information. Typical chemical composition and mechanical properties are based on the test results of the electrode in the typical welding conditions. The actual results may vary due to the welding conditions. No data is to be construed as recommendation for any welding condition or technique not controlled by Tien Tai Electrode Co., Ltd.