

## Characteristics and Applications:

TH-950HCR deposits the weld metal (30%Cr, 5%C) consists of primary carbides in a matrix of austenite-carbide eutectic. It can be used on carbon, low alloy, stainless steel, and manganese. The weld metal exhibits high hardness, good corrosion resistance, resistance to severe earth abrasion. It is suitable for crusher rolls, plates and Jaws, sleeves, cement mill part, conveyor screw, blades.

## Notes on usage:

1. Dry the electrodes at 300-350°C for 30-60 minutes before using. Agitator blade
2. Clean up the contaminations on the base metal to avoid porosity and crack.
3. Use back-step method and stay for 3-5 seconds before every end-up to prevent arc starting from blowholes.
4. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method.
5. Deposits should be limited to 2 layers.

## Typical chemical composition of weld metal (wt%):

C	Mn	Si	Cr
5.5	2.2	0.32	30.0

## Typical hardness of weld metal:

Testing Condition ( As Welded)	Vicker's Hardness (HV)	Rockwell's Hardness (HRC)	Shore's Hardness (HS)
Interpass temp. 150	700	60	81
Continuous welding	680	59	80

## Welding position:

## Sizes and recommended current range (AC or DC+):

Diameter (mm)	3.2	4.0	

COVE

disclaims any liability

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability for any loss or damage, including consequential, special, or exemplary damages, that may result from the use of the information contained herein. The information is provided for informational purposes only and is not intended to be used as a substitute for professional engineering advice. Other parts and procedures may be required for proper installation and use of the product. For more information, please contact our sales department at 886-6-2664301.

717, Taiwan

 TIENTAI

No.6, Kaifa 4th Rd., Rende Dist., Tainan Ci  
TEL: 886-6-2663721 / FAX: 886-6-2664301