

# TH-MN

AWS A5.13 EFeMn-A

## Characteristics and Applications:

TH-MN deposits the weld metal of high 13Mn austenitic structure for repair welding. The weld metal provides good crack resistance due to the Ni (3%) content. Work hardening, tensile strength, toughness and mechanical properties are excellent and available for machining and cutting after welding.

## Notes on usage:

1. Dry the electrodes at 150-200 for 30-60 minutes before using.
2. When the base metal (13%Mn steel) is hardened, remove off the hardened zone before Welding. Low current without pre-heating are recommended during welding.
3. Clean up the contaminations on the base metal to avoid porosity and crack.
4. Use back-step method to prevent arc starting from blowholes and hold for 3-5 seconds at every end-up.
5. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method.
6. Austenitic stainless stick electrode (ex TS-309/309L) is recommended for root pass of high-carbon steel and low-alloy steel.



Crusher Cone

		18	3.1
--	--	----	-----

## Typical hardness of weld metal:

Testing Condition	Vicker's Hardness (HV)	Rockwell's Hardness (HRC)	Shore's Hardness (HS)
Work Hardening	490	48	65

## Welding position:



## Sizes and recommended current range (AC or DC + ):

Diameter (mm)	3.2	4.0	5.0
Length (mm)	350	350	450
Amps	90-140	140-190	190-240

RED ELECTRODES

td. expressly disclaims any liability

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., L