

Characteristics and Applications:

TL-88B2 is an iron powder low hydrogen electrode. The weld metal contains 1.25%Cr-0.5%Mo that makes the electrodes more efficient at 550 , With the characters of stable arc, little spatter, complete slag covering, it's suitable for the welding of steel tube for heat transfer of boiler (STPA22,23, A335-P11,P12, A199T11 A200T11 A213T11 12), drawing steel (A387Gr11 12), casting iron (A217-WC6), and forging and forging steel (A182-F11,F12).

Notes on usage:

1. Clean up the contaminations on the base metal and welding seam so as not to derogate the weld metal quality from particles.
2. Dry the electrodes at 350-400°C for 60 minutes before using.
3. Use back-step method to prevent arc starting from blowholes and hold for 3-5 seconds at every end-up.
4. Maintain short arc length. Moving range should be controlled within 3 times of the wire's dia when you are welding with weave method.
5. Do not exceed the range of recommended current. Over heat input might decrease the impact value.
6. Pre-heat the workpiece at 150~300 and proceed PWHT at 620~700 .

Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Cr	Mo
0.06	0.65	0.18	0.016	0.008	1.21	0.50

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	PWHT
530(77)	625(91)	26	690°Cx1hr

warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability
 enTai Electrode Co., Ltd.

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or
 No data is to be construed as recommendation for any welding condition or technique not controlled by TI