

TL-581

AWS A5.1 E7018-1
EN ISO 2560-A-E 42 4 B 3 2 H10
JIS Z 3211 E4918-1

Characteristics and Applications:

TL-581 is an iron powder type of low hydrogen electrode for all-position welding of 490N/mm² grade high tensile steel. It performed with higher deposition rate, good X-ray soundness, good mechanical properties and smooth bead appearance. With excellent notch toughness at the temperature of -45°C, it is suitable for low alloy steels, medium carbon steels, heavy steel plates, cast steels and especially for welding of Aluminum Killed steel of LPG.

Notes on usage:

1. Dry the electrodes at 300-350°C for 60 minutes and then keep at 100-150°C before using.
2. Use back-step method to prevent arc starting from blowholes and hold for 3-5 seconds at every end-up.
3. Maintain short arc length. Moving range should be controlled within 3 times of the wire's dia when you are welding with weave method.
4. Clean up the contaminations on the base metal.


Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S
0.065	1.35	0.56	0.020	0.08

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -45°C (-50)
500(73)	580(84)	30	120(89)

Welding position:



Sizes and recommended current range (AC or DC<+>) :

Diameter (mm)	2.6	3.2	4.0	5.0
Length (mm)	350	350	350 450	450
Amps	F	80-110	90-130	140-180 170-240
	V&OH	70-100	80-120	120-160 150-180

The information contained or otherwise referenced herein is presented only as typical, without guarantee or warranty, and Tientai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. We do not assume any responsibility for any welding condition or technique not covered or specified by Tientai Electrode Co., Ltd.