

# TLH-88B2P

AWS A5.5 E8018-B2 H4  
EN ISO 3580-B-E5518-1CM H5  
JIS Z 3223 E5518-1CM H5

## Characteristics and Applications:

TLH-88B2P is an iron powder low hydrogen electrode. The weld metal contains 1.25%Cr-0.5%Mo that makes the electrodes more efficient at 550 °C. With the characters of stable arc, little spatter, complete slag covering, low hydrogen content, extremely low impurity, it's suitable for the welding of steel tube for heat transfer of boiler (STPA22,23, A335-P11,P12, A199T11 A200T11 A213T11 12), drawing steel (A387Gr11 12), casting iron (A217-WC6), and forging and forging steel (A182-F11,F12).

## Notes on usage:

1. Clean up the contaminations on the base metal and welding seam so as not to derogate the weld metal quality from particles.
2. Dry the electrodes at 350-400°C for 60 minutes before using.
3. Use back-step method to prevent arc starting from blowholes and hold for 3-5 seconds at every end-up.
4. Maintain short arc length. Moving range should be controlled within 3 times of the wire's dia when you are welding with weave method.
5. Do not exceed the range of recommended current. Over heat input might decrease the impact value.

## Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Cr	Mo
0.085	0.61	0.19	0.010	0.007	1.13	0.53

## Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -20°C (0 °C)	PWHT
560(82)	630(91)	26	100(74)	690°Cx1hr

## Welding position:



## Sizes and recommended current range (AC or DC<+>):

Diameter (mm)	3.2	4.0	5.0	
Length (mm)	350	350	450	
Amps	F	90-140	140-190	190-240
	V&OH	90-110	130-160	-

No guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability for damages resulting from the use of the information contained herein. All rights reserved. This document is controlled by TienTai Electrode Co., Ltd.

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty. It is not to be construed as a recommendation for any welding condition or technique not specifically mentioned. No data is to be construed as recommendation for any welding condition or technique not specifically mentioned.