

# TS-308LB

AWS A5.4 E308L-15  
EN ISO 3581-B-ES308L-15  
JIS Z3221 ES308L-15

## Characteristics and Applications:

The weld metal of TS-308LB is an austenite microstructure containing controlled  $\delta$  ferrite. The welding can be done in all positions with good X-ray soundness and good mechanical properties. It produces good notch toughness at the temperature as low as -196 W. The electrode is designed for welding of LNG tank.

## Notes on usage:

1. Dry the electrodes at 300-350 W for 60 minutes and keep it at 100-150 W before using.
2. To make the cooling time as short as possible between 500-800 W to prevent the intergranular corrosion.
3. Clean up the contaminations on the base metal, groove and pass to pass with stainless steel brush.
4. Use small heat input to reduce dilution, prevent cracking and improve impact value.

## Typical chemical composition of weld metal (wt%) :

C	Mn	Si	P	S	Cr	Ni
0.039	1.10	0.60	0.023	0.01	18.7	10.3

## Typical mechanical properties of weld metal :

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -196°C (-320 °F)
400(58)	580(84)	45	35(26)

## Welding position:



## Sizes and recommended current range ( AC or DC ) :

Diameter (mm)	2.6	3.2	4.0	4.8
Length (mm)	300	350	350	350
Amps	F	60-90	80-130	130-170
	V&OH	50-80	70-110	100-130

Tientai Electrode Co., Ltd. expressly disclaims any liability for the information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Tientai Electrode Co., Ltd. does not assume any responsibility for the information from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other welding conditions and procedures may produce different results.

No data is to be construed as recommendation for any welding condition or technique not controlled by Tientai Electrode Co., Ltd.

No. 6, Kaifu 4th Rd., Bund  
Dist. Taichung City 717, Taiwan  
TEL: 886-6-2664301



No. 6, Kaifu 4th Rd., Bund  
TEL: 886-6-2663721 / FAX: 886-6-2664301  
E-mail: twtred@itweld.com  
http://www.tientai.com