

TS-309Mo/ TS-309LMo

AWS A5.4 E309Mo/E309LMo-16
EN ISO 3581-B-ES309Mo-16/
EN ISO 3581-B-ES309LMo-16
JIS Z 3221 ES309LMo-16

Characteristics and Applications:

TS-309Mo/TS-309LMo is superior to TS-309/309L in crack resistance and corrosion resistance at the high temperature due to higher Mo content. Low carbon content of weld metal makes it suitable for dissimilar metal welding of joining mild steel to stainless steel and reducing inter-granular corrosion.

Notes on usage:

1. Clean up the contaminations on the base metal, groove and pass to pass with stainless steel brush.
2. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method.
3. Dry the electrodes at 250~300 for 60 minutes before using. Take out consumables for half day consumption and keep in the environment at 100~150 during welding process.
4. Use lower current to prevent from cracking and minimize base metal dilution whiling in welding dissimilar metals or root pass of clad steel.


Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Cr	Ni	Mo
0.025	0.90	0.65	0.034	0.016	22.5	13.50	2.40

Typical mechanical properties of weld metal:

Tensile strength MPa(ksi)	Elongation %
630(91)	40

Welding position:



Sizes and recommended current range (AC or DC +):

Diameter (mm)		2.6	3.2	4.0	4.8
Length (mm)		300	350	350	350
Amps	F	60-90	80-130	130-170	180-210
	V&OH	50-70	70-110	100-130	-

COVERED ELECTRODES

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TianTai Electrode Co., Ltd. expressly disclaims any liability for any loss or damage, including consequential damages, incurred from any use of these products. Typical data is obtained when welded and tested in accordance with AWS specification. Other tools and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TianTai Electrode Co., Ltd.