TS-310Mo

Characteristics and Applications:

Heat resistance corrosion and toughness of TS-310Mo are excellent. The weld metal is a full austenite structure containing 25%Cr-20%Ni. It is not necessary to pre-heat and post-weld heat treatment. It is suitable for the dissimilar metals welding, low-temperature service stainless steel, AISI 310S steel, mild steel, and Cr-Mo steel.

Notes on usage:

- 1. Be sure to clean up the contaminations on the base metal, groove and pass to pass with stainless steel brush.
- 2. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method.
- 3. Dry the electrodes at 250~300 for 60 minutes before using. Take out a batch of half day consumption and keep in the environment at 100~150 during welding process.
- 4. Due to the austenitic matrix containing intensive Cr, Ni, use lower current and maintain temperature under 150 to prevent from cracker caused by high temperature.

Typical chemical composition of weld metal (wt%):

С	Mn	Si	Р	S	Cr	Ni	Мо
0.10	1.80	0.30	0.030	0.010	25.1	20.5	2.40

Typical mechanical properties of weld metal:

Tensile strength	Elongation
MPa(ksi)	%
600(87)	31

Welding position:



Sizes and recommended current range (AC or DC +):

Diameter (mm)		2.6	3.2	4.0	4.8
Length (mm)		300	350	350	350
Amps	F	60-90	80-130	130-170	180-210
	V&OH	50-70	70-110	100-130	-

d , exoresely disclaime apriliability, . Luce may preduce different results. The information contained or otherwise referenced hereig is presented only as "Unical" without duration or unarranted or the soft TeesTa, Electrode C is presented for the soft of the

<u>City 717 Taiwan</u>