

TS-312SB

Characteristics and Applications:

The weld metal of TS-312SB is a stainless steel containing more ferrite content than TS-309/309L. Good crack resistance. It is excellent for the welding of dissimilar metals, cladding steel and steels with high harden ability. Due to higher ferrite, TS-312SB is low sensitive to cracking and especially suitable for welding dissimilar metals, hardening alloy steel and metals with poor weldability or easy to cause porosity. However, High temperature should be avoided for not to cause cracks resulted from embrittlement effect of second phase.

Notes on usage:

1. Clean up the contaminations on the base metal, groove and pass to pass with stainless steel brush.
2. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method.
3. Dry the electrodes at 250~300 for 60 minutes before using. Take out consumables for half day consumption and keep in the environment at 100~150 during welding process.
4. Use lower current to prevent from crack and minimize base metal dilution.

Typical chemical composition of weld metal (wt%):

| C | Mn | Si | P | S | Cr | Ni |
|------|-----|-----|-------|-------|------|-------|
| 0.10 | 1.2 | 0.9 | 0.025 | 0.037 | 28.7 | 10.30 |

Typical mechanical properties of weld metal:

| Tensile strength MPa(ksi) | Elongation % |
|------------------------------|-----------------|
| 790(115) | 24 |

Welding position:



Sizes and recommended current range (AC or DC +):

| Diameter (mm) | 2.6 | 3.2 | 4.0 | 4.8 | |
|---------------|------|-------|--------|---------|---------|
| Length (mm) | 300 | 350 | 350 | 350 | |
| Amps | F | 60-90 | 80-130 | 130-170 | 180-210 |
| | V&OH | 50-70 | 70-110 | 100-130 | - |

we do not assume any liability for any damages or results.

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Tien Tai Electrode Co., Ltd. expressly disclaims any liability for any damages or results incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by Tien Tai Electrode Co., Ltd.

717, Taiwan



No. 6, Kaifa 4th Rd., Rende Dist., Tainan City
TEL: 886-6-2663721 / FAX: 886-6-2664301
E-mail: twtrad@tieweld.com
http://www.tientai.com.tw

1706