TS-318

AWS A5.4 E318-16 EN ISO 3581-B-ES318-16 JIS Z 3221 ES318-16

Characteristics and Applications:

The weld metal of TS-318 is a modified 316 stainless steel containing Nb. It provides good corrosion resistance to sulfuric acid and organic acid due to its Mo and Nb content. It is suitable for chemical vessels, pipeline, and specifically suitable for steel plate welding of AISI 316Ti / SUS 316-Ti.

Notes on usage:

- 1. Clean up the contaminations on the base metal, groove and pass to pass with stainless steel brush.
- 2. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method..
- 3. Dry the electrodes at 250~300 for 60 minutes before using. Take out consumables for half day consumption and keep in the environment at 100~150 during welding process.
- 4. Use lower current to prevent from crack and minimize base metal dilution.

Typical chemical composition of weld metal (wt%):

С	Mn	Si	Р	S	Cr	Ni	Мо	Nb
0.025	0.70	0.75	0.04	0.010	18.50	12.00	2.50	0.40

Typical mechanical properties of weld metal:

Tensile strength	Elongation
MPa(ksi)	%
600(87)	41

Welding position:











Sizes and recommended current range (AC or DC +):

Diameter (mm)		2.6	3.2	4.0	4.8
Length (mm)		300	350	350	350
A	F	60-90	80-130	130-170	180-210
Amps	V&OH	50-70	70-110	100-130	-

al, without quaractes or <u>warracturant Tier Ta</u>r Electrode Co., 114, express bug al un coordana with AN Erracetination. Who the Nood unconsure may pro ique matematicaled by Tien Tar Electrode Co., Etd.