



AWS A5.4 E410-16
EN ISO 3581-A-E 13 R 1 2
JIS Z 3221 ES410-16



TS-410 is suitable for welding the AISI 410 and AISI 420 series of stainless steels. Owing to their hardenability and it easy to crack in weld bead or HAZ, pre-heat and PWHT are both highly recommended. The product provides good oxidization and corrosion resistance . It is suitable for petroleum refining plants and chemical plants. It is also applicable for corrosion and wear resistance of carbon steel.



1. Clean up the contaminations on the base metal, groove and pass to pass with stainless steel brush.
2. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method..
3. Dry the electrodes at 250~300 for 60 minutes before using. Take out consumables for half day consumption and keep in the environment at 100~150 during welding process.
4. Use lower current to prevent from cracking and minimize base metal dilution.
5. Pre-heat at 200-250 , and post-weld heat treatment at 700-800 .




:

C	Mn	Si	P	S	Cr	Ni
0.02	0.30	0.60	0.025	0.010	13.0	0.30



:

Tensile strength MPa(ksi)	Elongation %	PWHT
520(75)	23	750 x1hr



+)

Diameter (mm)		2.6	3.2	4.0	4.8
Length (mm)		300	350	350	350
Amps	F	60-90	80-130	130-170	180-210
	V&OH	50-70	70-110	100-130	-

The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Tientai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may vary. No data is to be construed as recommendation for any welding condition or technique not controlled by Tientai Electrode Co., Ltd.

Taiwan



No. 6, Kaifu 4th Rd., Rende Dist., Taichung City, Taiwan
TEL: 886-6-2663721 / FAX: 886-6-2664301
E-mail: twtrad@itw weld.com
http://www.tientai.com