

TS-2209

AWS A5.4 E2209-16
EN ISO 3581-B-ES2209-16
JIS Z 3221 ES2209-16

Characteristics and Applications:

TS-2209 is designed to weld duplex stainless steels such as UNS S31803 (Alloy 2205). It provides excellent pitting corrosion resistance, stress corrosion resistance and crack resistance. It is suitable for welding application of heat exchanger, chemical equipments and pipes.

Notes on usage:

1. Be sure to clean up the contaminations on the base metal, groove and pass to pass with stainless steel brush.
2. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method..
3. Dry the electrodes at 250~300 for 60 minutes before using. Take out a batch of half day consumption and keep in the environment at 100~150 during welding process.
4. Use lower current to prevent from crack and minimize base metal dilution.

Typical chemical composition of weld metal (wt%) :

C	Mn	Si	P	S	N	Cr	Ni	Mo
0.025	1.00	0.60	0.035	0.015	0.14	22.2	9.0	3.2

Typical mechanical properties of weld metal :

Tensile strength MPa(ksi)	Elongation %
785(114)	28

Welding position:



Sizes and recommended current range (AC or DC +):

Diameter (mm)		2.6	3.2	4.0	4.8
Length (mm)		300	350	350	350
Amps	F	60-90	80-130	130-170	180-210
	V&OH	50-70	70-110	100-130	-

expressly disclaims any liability
as may produce different results.

The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Tien Tai Electrode Co., Ltd.
incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures
may not be performed by the manufacturer or intended end user. All technical data is subject to change without notice.

City 717, Taiwan



No. 6, Kaifu 4th Rd., Rende Dist., Taipei
TEL: 886-6-2663721 / FAX: 886-6-2664301
E-mail: twtred@itwworld.com
http://www.tientai.com.tw 1706