

ArcStar T12

AWS A5.20 E71T-1CJ / E71T-12CJ
EN ISO 17632-A-T 46 4 P C1 1 H5

Characteristics and Applications:

ArcStar T12 is a gas-shielded flux cored wire designed for mild steel and 490N/mm² high tensile steel. It is suitable for all position welding. Its features include stable arc, less spatter, easy slag removable, excellent X-Ray inspection, low diffusible hydrogen (less than 5 ml/100g) and good low temperature impact value due to 0.4%Ni in weld metal. The typical applications are shipbuilding, offshore, storage tank, pressure vessels, piping etc.

Notes on Usage:

1. Use DC(+) polarity.
2. Use CO₂ as shielding gas.
3. Maintain interpass temperature under 150°C in multi-pass welding to keep excellent mechanical properties.
4. Keep the product dry, while it is stored or delivered.


Typical chemical composition of weld metal (wt%)

C	Mn	Si	P	S	Ni
0.04	1.13	0.23	0.009	0.005	0.41

Typical mechanical properties of weld metal

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf)		PWHT
529(77)	574(83)	30	-40 (-40)	169(125)	--
490(71)	550(80)	32	-46 (-50)	116(86)	610 ×13hrs

Welding position



Sizes and recommended parameter range (DC +):

Stick out : 15-25 (mm), gas flow rate : 20-25 (l/min)

Position	Diameter (mm)	1.2
F, HF		160A~280A / 24V~33V
VU, OH		150A~220A / 24V~28V
VD		230A~280A / 28V~33V
H		200A~260A / 26V~30V

ed herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability, expressed or implied, resulting from the use of this information. The data contained herein is based on tests and results obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.

* The information contained or otherwise referred to herein is based on tests and results obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.

