FabStar 721

AWS A5.26 EG72T-1

Characteristics and Applications:

FabStar 721 is a self-shielded flux-cored wire used for single pass, vertical up, electrogas welding of shipbuilding, heavy equipment fabrication and structural welding and storage tank. It is suitable for welding of mild steel and high tensile steels with high deposition rate and with or without consumable guide.

Notes on u sage:

- 1. Use DC(+) polarity.
- 2. Composition of consumable guide tube should be as close as possible to parent steel and be aware to add an insulating ring to the tube made without insulating coating to prevent from a short circuit.
- 3. Mechanical properties depend on plate chemistry and joint geometry.
- 4. Pre-heat the workpiece and star-up zone.
- 5. Baffle plate should be tightened firmly to prevent a leak of deposited metal.
- 6. Control all parameters with cares during welding, such as shape of weld joint, tube material, cooling rate.
- 7. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%)

С	Mn	Si	Р	S	Мо	
0.05	1.50	0.35	0.015	0.007	0.18	

Typical mechanical properties of weld metal on A36 base metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -30°C(-20 ²)
441(64)	540(78)	25	50(37)

Sizes and recommended current range (DC pË+pĺ):

Diameter (mm) Parameters	1.6		2.4		3.0			
Thickness	9	12	12	19	19 🚈	25'''	38,	50
Wire Feed Speed (cm/min)	280	300	350	400	510	580	750趧	890
Voltage(Volt)	30	32	36	38	35-38	38-40	42-44	42-44

change contained or otherwise retailed by seven some as two rat, without quaragles of warraght, and, tien tast is cross to response any labour or from any reliance, thereon. Typical data is obtained when welded and tested in accordance with AVIS specification. Other tests and procedures may produce different results at a 1s to be construed as recommendation for any welding condition or technique not controlled by Tien Tai Electrode Co., Ltd.

