

TFW-308H

AWS A5.22 E308HT1-1
JIS Z 3323 TS 308H-F C 1 1

Characteristics and Applications:

TFW-308H is special for 100% CO₂ gas and all-position welding. It owns excellent slag release. An 19Cr-9Ni austenitic stainless steel deposited can be used for joining 18Cr-8Ni austenitic steels such as AISI304. AISI301. 302. SUS304H. It provides good resistance to inter-granular corrosion and has higher tensile strength than TFW-308L. It also can be used as an intermediate layer for hardfacing.

Notes on usage:

1. Before welding, oil, rusty, and moisture should be cleaned off the base material that should have the proper protection from the wind in welding site.
2. Use 99.8% purity or higher CO₂ shielding gas.
3. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Cr	Ni
0.05	1.50	0.50	0.023	0.008	19.90	9.80

Typical mechanical properties of weld metal:

Tensile strength MPa(ksi)	Elongation %
586(85)	40

Welding position:



Sizes and recommended parameter range (DC +):

Stick out:15-20(mm),flow rate:20-25(l/min):

Position \ Diameter (mm)	1.2
F	140-220A / 23~33V
H	140-220A / 23~33V
VU OH	120-200A / 24~30V

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.