

## Characteristics and Applications:

TFW-308LT is designed for Flat position welding by gas shield of 100% CO<sub>2</sub>. It has very excellent slag-removal property. An austenitic stainless steel deposit that can be used for joining common austenitic steels such as Types 304,304L, 321, CF-8, and CF-3. It provides good resistance to intergranular corrosion.

## Notes on usage:

1. Before welding, the base material should be cleaned from oil, rusty, moisture and it should have the proper protection from the wind in welding site.
2. Use with 100% CO<sub>2</sub>.
3. Keep the product dry, while it is stored or delivered.

## Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Cr	Ni
0.025	1.53	0.56	0.023	0.008	19.31	9.63

## Typical mechanical properties of weld metal:

Tensile strength MPa(ksi)	Elongation %
------------------------------	-----------------

\*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.