

TFW-308LTM

AWS A5.22 E308LT0-4
EN ISO 17633-A-T 19 9 L R M21 3
JIS Z 3323 TS 308L-F M2 1 0

Characteristics and Applications:

TFW-308LTM is designed for Flat position welding by gas shield of mix gas (75 80% Argon and 25 20% CO₂). It features excellent slag-removal property. An austenitic stainless steel deposit can be used for joining common austenitic steels such as Types 304,304L, 321, CF-8, and CF-3. It provides good resistance to intergranular corrosion.

Notes on usage:

1. Before welding, oil, rusty, and moisture should be cleaned off the base material that should have the proper protection from the wind in welding site.
2. Use with mix gas (75 80% Argon and 25 20% CO₂).
3. Keep the product dry, while it is stored or delivered.


Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Ni	Cr
0.024	1.60	0.53	0.022	0.007	9.56	19.5

Typical mechanical properties of weld metal:

Tensile strength MPa(ksi)	Elongation %
586(85)	38

Welding position:



Sizes and recommended parameter range (DC +):

Stick out:15-20(mm),flow rate:20-25(l/min):

Diameter (mm)	1.2
Position	
F, HF	130A-220A/24V-33V

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.