

# TFW-316LT

AWS A5.22 E316LT0-1  
EN ISO 17633-A-T 19 12 3 L R C 1 3  
JIS Z 3323 TS 316L-F C 1 0

## Characteristics and Applications:

TFW-316LT is designed for flat position welding by gas shield of CO<sub>2</sub> gas. An austenitic stainless steel deposited that can be used for joining Types 316,316L stainless steels. It provides high resistance to intergranular corrosion with low carbon weld deposit.

## Notes on usage:

1. Before welding, the base material should be cleaned from oil, rusty, moisture and it should have the proper protection from the wind in welding site.
2. Use 99.8% purity or higher CO<sub>2</sub> shielding gas. Maintain the flow rate not less than 20L/min when wire diameter is 1.2 mm.
3. Keep the product dry, while it is stored or delivered.

## Typical chemical composition of weld metal (wt%):

C	Mn	Si	P				
27	1.25	0.68	0.025	0.006	2.27	11.4	18.6

## Typical mechanical properties of weld metal:

Tensile strength MPa(ksi)	Elongation %
558(81)	38

## Welding position:



## Size and recommended parameter range (DC + )

Stick out: 18-25 (mm), flow rate:20-25(l/ min):

Diameter (mm)	
1.2	
Position	
F, HF	130A-220A/24V-33V

\*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.