

# TM-77

AWS A5.18 E70C-6M  
EN ISO 17632-A-T 46 4 M M21 3 H5  
JIS Z 3313 T 49 4 T15-0 M A-U

## Characteristics and Applications:

TM-77 is a gas-shielded metal-cored wire that features smooth spray arc, low slag volume, low spatter, low diffusible hydrogen low fume emission and excellent low temperature impact toughness down to -40°C. It welds with a wider penetration profile and higher deposition efficiency than solid wire.

Multi-layer welding can be performed without removing slag. It is suitable for steel structures, storage vessels and multi-layer welding on heavy plate thickness.

## Notes on usage:

1. Use DC(+) polarity.
2. Ar-CO<sub>2</sub> mixture. 75%~80%Ar 25%~20%CO<sub>2</sub>.
3. Inter-pass temperature should be under 150 °C while in multiple-pass welding.
4. Keep the product dry, while it is stored or delivered.

## Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S
0.04	1.45	0.54	0.010	0.008

## Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -40°C(-40 °F)
480(70)	550(80)	26	65(48)

## Welding position:



## Sizes and recommended current range ( DC + ):

Stick out: 15-25 (mm) flow rate: 20-25 (l/min)

Parameters	Diameter (mm)	1.2	1.4	1.6
F, H		240A-320A/26V-34V	260A-340A/27V-34V	270A-360A/ 28V-35V

as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability for any damages resulting from the use of this information. Other factors such as welding procedures may produce different results.

\* The information contained or otherwise referenced herein is presented only for general guidance. It is the responsibility of the user to determine its suitability for a particular application. The user shall assume all risk and responsibility for any use of the information contained herein. No data is to be construed as recommendation for any welding condition.

