

TMS-410NiMo

AWS A5.22 EC410NiMo

Characteristics and Applications:

TMS-410NiMo is a gas-shielded metal-cored wire. It is low hydrogen levels and excellent impact toughness at 0 ϕ . It is generally used for welding of ASTM CA6NM castings, materials, with similar composition, and turbines of hydro plant.

Notes on usage:

1. Before welding, oil, rusty, and moisture should be cleaned off the base material that should have the proper protection from the wind in welding site.
2. Use with mix gas (75q 80% Argon and 25q 20% CO₂).
3. Require pre-heat and inter-pass temperature 150 ϕ q 260 ϕ , and post weld heat treatment.

Typical chemical composition of weld metal (wt%) :

C	Mn	Si	P	S	Cr	Ni	Mo
0.031	0.45	0.29	0.009	0.008	11.70	4.50	0.50

Typical mechanical properties of weld metal :

Tensile strength MPa(ksi)	Elongation (%)	Charpy V-Notch J (ft-lbf) 0°C (32 °)	PWHT
860(125)	20	38(28)	610 W Ø1hr

Welding position:



Sizes and recommended parameter range (DCpE+pl):

Stick out:15 -20(mm),flow rate:20 -25(l/min):

Position	Diameter (mm)	1.2
F, HF		180A-250A/24V-28V

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.