

TWE-715

AWS A5.20 E71T-5C
EN ISO 17632-A-T 46 3 P C1 1 H10

Characteristics and Applications:

TWE-715 is an all-position flux-cored wire designed to be used with CO₂ gas for 490N/mm² grade high tensile steel. Its low temperature impact toughness is better than E71T-1(AWS A5.20). The typical applications of TWE-715 are constructional steel, machinery and shipbuilding.

Notes on usage:

1. DC(+) polarity is recommended.
2. Use CO₂ as shielding gas.
3. Keep inter-pass temperature under 150 when you are in multiple-pass welding.
4. Keep the product dry, while it is stored or delivered.


Typical chemical composition of weld metal (wt%)

C	Mn	Si	P	S
0.05	1.30	0.45	0.015	0.007

Typical mechanical properties of weld metal

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -30°C(-20)
493(72)	562(82)	30	65(48)

Welding position:



Sizes and recommended current range (DC +):

Stick out:15-25(mm),flow rate:20-25(l/min):

Diameter (mm)	1.2	1.6
Parameters		
F	130A~300A / 24V~36V	160A~340A / 24V~38V
HF	130A~300A / 24V~36V	160A~340A / 24V~38V
H	130A~300A / 24V~36V	160A~340A / 24V~38V
VU, OH	130A~300A / 24V~36V	160A~340A / 24V~38V
VD	230A~280A / 28V~33V	250A~320A / 28V~32V

as typical, without guarantee or warranty, and Tien Tai Electrode Co., Ltd. expressly disclaims any liability, and tested in accordance with AWS specification. Other lists and procedures may produce different results. No data is to be construed as recommendation for any welding condition.

The information contained or otherwise referenced herein is presented only for informational purposes and is not intended to be construed as a recommendation for any welding condition. No data is to be construed as recommendation for any welding condition.