TWE-811Ni1

AWS A5.29 E81T1-Ni1C EN ISO 17632-A-T 46 3 1Ni P C1 1 H10

Characteristics and Applications:

TWE-811Ni1 is a titania type flux-cored wire with CO2 shielding gas for all-position welding. It is designed for welding 590 N/mm² high tensile steel used in low temperatures.

It provides good weldability with smooth bead appearance, less spatter and stable arc as well as good impact properties down to -30

It is also suitable for welding on construction machinery, shipbuilding, offshore, structures, bridges, storage tanks and piping.

Notes on usage:

- 1. Excessive heat input should reduce impact value. Therefore, perform welding with selecting proper heat input based on the required impact value.
- 2. Must preheat at 50~150 depending on steels, plate thickness and restraint.
- 3. Use DC(+) polarity.
- 4. Use 99.8% or higher purity of CO₂ Gas.
- 5. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%):


С	Mn	Si	Р	S	Ni
0.04	1.20	0.25	0.015	0.009	1.00

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %			V-Notch (ft-lbf)	PWHT
602(87)	650(94)	26	T	·· -30 (-20)	110(81)	
002(87)	050(94)	20	Ш	-40 (-40)	95(70)	
522(76)	590(86)	30		-40 (-40)	92(68)	590 *8hr

Welding position:





Diameter (mm) Position	1.2	1.4	1.6		
F HF	180A-300A / 24V-36V	180A-350A / 24V-36V	200A-400A / 24V-38V		
VU OH	150A-220A / 22V-28V	150A-220A / 22V-28V	160A-220A / 22V-28V		
Н	150A-260A / 22V-31V	160A-280A / 22V-30V	180A-280A / 23V-32V		

* The information contained or otherwise referenced herein is presented only as "typical" we