

# TWH-12-S

## TF-81

### Characteristics and Applications:

TWH-12-S is a submerged arc flux-cored wire to provide a modified H12 tool steel deposit which retains hardness at high temperatures. TWH-12-S flux-cored wire is used with TF-81, a neutral flux, for submerged arc welding applications. The combination is suitable for work rolls, pinch rolls and surfaces subjected to sliding metal/metal wear.

### Notes on usage:

1. The DC(+) polarity is recommended.
2. The workpiece should be free of moisture to prevent porosity and enhance the interfacial bonding between parent steel and weld metal.
3. To prevent weld crack, the pre-heat and inter-pass temperatures should be between 204-316°C for massive workpieces, heavy cylinders and highly stressed workpieces..

### Typical chemical composition (wt%):

C	Mn	Si	Cr	Mo	V	W
0.23	1.6	0.6	6.1	1.3	0.2	1.2

### Typical weld metal hardness (on mild steel) :

Hardness (HRC)	47-53
----------------	-------

### Suggested welding parameter DC(<+>):

Parameters	Diameter (mm)	3.2
Volt		25-32
Amps		300-450
Stick out(mm)		30-40

LUX CORED WIRES

TienTai Electrode Co., Ltd. expressly disclaims any liability for any damage or injury incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results.

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results.

3rd. Floor, Dingyuan, Tielin, City 313, Zhejiang, China  
TEL: 886-6-2663721 / FAX: 886-6-2664301

No. 9, Keifan, 4th. Floor, Hangzhou, China