

TGA-80

AWS A5.28 ER80S-G
JIS Z3316 W 59 A 0U 0

Characteristics and Applications :

For all-position welding of 590N/mm² high tensile steel, it is suitable for root pass welding of pipes and commonly applied in welding Mn-Mo Mn-Mo-Ni alloy high tensile steel.

Notes on usage :

1. 100% Argon shielding gas with 99.997% high purity is recommended and the flow rate must be properly controlled. The recommended flow rate is 7-12l/min when arc current is 100-200Amp and it goes up to 12-15l/min when arc current rises to 200-300Amp.
2. Trailer Shield is required to ensure the weld pool completely shielded by inert gas until solidification is complete and no porosity problem.
3. Select right gas cup size and employ proper stick out of tungsten electrode.
4. Be sure to clean up the contaminations on the base metal and welding seam so as not to derogate the weld metal quality from particles.

Typical chemical composition of wire (wt%):

C	Mn	Si	P	S	Mo	Cu
0.08	1.56	0.67	0.015	0.012	0.50	0.02

Typical mechanical properties of all weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-1bf) 0°C (32)
650(94)	700(102)	24	200(148)

Sizes available:

Diameter (mm)	2.4
Length (mm)	915

SOLID WIRES

Information presented herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability for any damage or injury incurred when used in applications other than those specified herein. Other tests and applications may produce different results. This information is not intended as a recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.

* The information contained or otherwise referred to herein is for reference only. Typical data is not intended as a recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.



No.6, Kaifa 4th Rd., Rende Dist., Tainan City 717, Taiwan

TEL: +886-6-2937777 FAX: +886-6-2937778
E-MAIL: twt80@www.tientai.com.tw
http://www.tientai.com