Characteristics and Applications:

TF-250 is a high-basic agglomerated submerged arc flux. It is suitable for using DC+ single, AC single, DC+/AC and AC/AC. It provides excellent weld ability even in narrow groove. Due to its neutral behavior, good mechanical properties of weld metal can be controlled by using the appropriate wire grade.

With combination of low phosphorus wires (TSW-E22R or TSW-E23R), the X and J factors can be

controlled to satisfy the step cooling requirement.

- Heat treatable and heat resistant low-alloy CrMo steel
- Pressure vessel
- Fine grain structural steels for low temperature requirements
- High tensile fine grain steels

Notes on usage:

1. Dry the flux at 300~350 for 2~4hr holding time.

2. Adding proper quantity of new flux with the used one to maintain good quality of weld metal.

Typical chemical composition of weld metal (wt %):

Wire	EN ISO 24598-A	С	Si	Mn	Р	S	Cr	Мо	Cu	Note
TSW-E22	S 55 3 FB CrMo1	0.09	0.25	0.80	0.013	0.008	1.10	0.45	0.03	-

WIRE

270

UXES

and TienTai Electrode Co., Ltd. expressly disclaims any liability. ion. Other tests and procedures may produce different results. ie Co., Ltd.

^{*} The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specifical. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrod.



