

# TF-385

Basicity index: 0.6

EN ISO 14174 S A AR 1 78 AC H5

## Characteristics and Applications:

TF 385 is an agglomerated, low basicity flux with pick up of Mn and Si. It's suitable for welding with single and multiple wire process with AC as well DC. Has excellent bead appearance, resistant against porosity and excellent slag release.

- Shipbuilding
- Structural Steels
- LPG Cylinders

## Notes on usage:

1. The flux must be re-dried at a temperature of 300~350°C for 1~2hr holding time when it is affected by moisture pick-up.
2. Adding proper quantity of new flux with the used one to maintain good quality of weld metal.

## Typical chemical composition of weld metal (wt %) :

Wire	EN ISO 14171-A	C	Si	Mn	P	S	Mo
TSW-E12	S 50 Z AR S2Mo	0.05	0.7	1.5	0.03	0.012	0.43

## Typical mechanical properties of weld metal:

Wire	AWS A5.23	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf)	Temperature °C( )	Remark
TSW-E12	F9AZ-EA2-G	617(89)	656(95)	29	-	-	AW

id. expressly disclaims any liability.  
ures may produce different results.

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. incurs no liability from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.

n City 717, Taiwan.  
4301



No.6 Kaifa 4th Rd., Rende Dist., Tainan  
TEL:886-6-2663721 /FAX:886-6-266  
E-mail:twta@ttweld.com  
http://www.tientai.com

1902