

Characteristics and Applications:

TFS-300 is a neutral bonded flux, which has good weldability, excellent slag removal and smooth bead appearance. Some alloys were suitably added to maintain the stability of the alloy content in weld metal. It features very sophisticated mechanical properties and corrosion resistibility.

- Stainless308, 308L, 316 and 316L butt join.
- Pressure vessel

Notes on usage:

1. Use low heat input to keep the corrosion resistibility and mechanical properties on heat-affected zone unchanged.
2. Bake at 200~300°C for 1-2hr before use.
3. Add reasonable new flux when recycle the used flux so as to maintain good welding quality.

Typical chemical composition of weld metal (wt %):

Wire	C	Mn	Si	P	S	Cr	Ni	Mo
TW-308L	0.04	1.50	0.46	0.020				

The information contained herein is a reference only and is not intended to be used as a basis for any warranty, liability, or other legal obligation. Tientai Electrode Co., Ltd. does not assume any liability for any loss or damage incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by Tientai Electrode Co., Ltd.